

# CarTech® 440B Stainless

## Identification

UNS Number

- S44003

## Type Analysis

Single figures are nominal except where noted.

<b>Carbon</b>	0.75 to 0.95 %	<b>Manganese (Maximum)</b>	1.00 %
<b>Phosphorus (Maximum)</b>	0.040 %	<b>Sulfur (Maximum)</b>	0.030 %
<b>Silicon (Maximum)</b>	1.00 %	<b>Chromium</b>	16.00 to 18.00 %
<b>Molybdenum (Maximum)</b>	0.75 %	<b>Iron</b>	Balance

## General Information

Description

This high-carbon chromium steel is designed to provide stainless properties with excellent hardness. In some respects it behaves similarly to tool steels. CarTech 440B stainless attains a hardness of Rockwell C 58 when heat treated and has been used for cutlery, hardened balls and similar parts. This steel makes fair permanent magnets.

Elevated Temperature Use

Carpenter Stainless type 440B is not usually recommended for elevated temperature applications since corrosion resistance is reduced when used in the annealed condition or hardened and tempered above about 800°F (427°C).

## Corrosion Resistance

Carpenter Stainless Type 440B has corrosion resistance generally similar to that of Type 410. It has resisted corrosion from mild atmospheres, fresh water, steam, ammonia, many petroleum products and organic materials and several mild acid environments.

This grade is used in the hardened plus tempered condition. Optimum corrosion resistance is obtained with a temper below about 800°F (427°C).

For optimum corrosion resistance, surfaces must be free of scale, lubricants, foreign particles, and coatings applied for drawing and heading. After fabrication of parts, cleaning and/or passivation should be considered.

**Important Note:** The following 4-level rating scale is intended for comparative purposes only. Corrosion testing is recommended; factors which affect corrosion resistance include temperature, concentration, pH, impurities, aeration, velocity, crevices, deposits, metallurgical condition, stress, surface finish and dissimilar metal contact.

Nitric Acid	Moderate	Sulfuric Acid	Restricted
Phosphoric Acid	Restricted	Acetic Acid	Restricted
Sodium Hydroxide	Moderate	Salt Spray (NaCl)	Restricted
Humidity	Good		

## Properties

### Physical Properties

Specific Gravity	7.65
Density	0.2760 lb/in <sup>3</sup>
Mean Specific Heat (32 to 212°F)	0.1100 Btu/lb/°F
Mean CTE (32 to 212°F)	5.60 x 10 <sup>-6</sup> in/in/°F
Electrical Resistivity (70°F)	361.0 ohm-cir-mil/ft

## CarTech® 440B Stainless

### Typical Mechanical Properties

#### Typical Room Temperature Mechanical Properties

Hardened 1900°F (1038°C), oil quench, tempered 600°F (316°C)

0.2% Yield Strength		Ultimate Tensile Strength		% Elongation in 2" (50.8 mm)	% Reduction of Area	Brinell Hardness
ksi	MPa	ksi	MPa			
270	1862	280	1931	3	15	534

### Heat Treatment

#### Annealing

For maximum softness, this steel should be heated uniformly to 1550/1600°F (843/871°C). Soak and cool very slowly in the furnace. Brinell approximately 223. Intermediate or process annealing treatment-heat uniformly to 1350/1400°F (732/760°C). Air cool. Brinell hardness approximately 241.

#### Hardening

Heat to 1850/1950°F (1010/1066°C); soak; quench in warm oil or cool in air. Do not overheat. When overheated, full hardness cannot be obtained.

#### Tempering

Hardness of approximately Rockwell C 58/59 will be obtained. To remove peak stresses and yet retain maximum hardness, temper at least one hour at 300/350°F (149/177°C°).

#### Typical Hardness

1" (25.4 mm) round hardened 1900°F (1038°C), oil quench, tempered one hour

Tempering Temperature		Rockwell C Hardness
°F	°C	
300	149	58/59
400	204	56/57
500	260	53/54
600	315	53
700	371	54
800	427	54

For maximum corrosion resistance, this steel should not be tempered above 800°F (427°C).

### Workability

#### Hot Working

This steel should be handled like high-speed tool steel. Preheat to 1400/1500°F (760/816°C), then heat slowly and uniformly to 1900/2150°F (1038/1177°C). Do not forge below 1700°F (927°C), and reheat as often as necessary. Cool in a furnace, if possible, or in warm dry lime or ashes. Anneal after forging: cool to room temperature before annealing.

#### Cold Working

If annealed for maximum softness, this steel can be moderately cold formed, headed and upset.

#### Machinability

For most machining operations, this steel cuts best when in the dead soft annealed condition. Due to its high carbon content, it machines somewhat like high-speed steel. Because chips are tough and stringy, chip curlers and breakers are important.

Following are typical feeds and speeds for Carpenter Stainless Type 440B.

## CarTech® 440B Stainless

### Turning—Single-Point and Box Tools

Depth of Cut (Inches)	High Speed Tools			Carbide Tools (Inserts)			
	Tool Material	Speed (fpm)	Feed (ipr)	Tool Material	Speed (fpm)		Feed (ipr)
					Uncoated	Coated	
.015	T15	75	.015	C6	325	375	.015
.025	M42	80	.007	C7	400	500	.007

### Turning—Cut-Off and Form Tools

Tool Material		Speed (fpm)	Feed (ipr)						
High Speed Tools	Carbide Tools		Cut-Off Tool Width (inches)			Form Tool Width (inches)			
			1/16	1/8	1/4	1/2	1	1 ½	2
M2	C6	55	.001	.001	.0015	.001	.001	.001	.0005
		205	.004	.0055	.007	.005	.004	.0035	.0035

### Rough Reaming

High Speed		Carbide Tools		Feed (ipr) Reamer Diameter (inches)					
Tool Material	Speed (fpm)	Tool Material	Speed (fpm)	1/8	1/4	1/2	1	1 ½	2
T15	65	C2	85	.003	.006	.010	.015	.018	.021

### Drilling

High Speed Tools		Feed (inches per revolution) Nominal Hole Diameter (inches)							
Tool Material	Speed (fpm)	1/16	1/8	1/4	1/2	3/4	1	1 ½	2
		T15, M42	45-55	.001	.003	.006	.010	.014	.017

### Die Threading

FPM for High Speed Tools				
Tool Material	7 or less, tpi	8 to 15, tpi	16 to 24, tpi	25 and up, tpi
T15, M42	5-12	8-15	10-20	15-25

### Milling, End-Peripheral

Depth of Cut (inches)	High Speed Tools						Carbide Tools					
	Tool Material	Speed (fpm)	Feed (ipt) Cutter Diameter (in)				Tool Material	Speed (fpm)	Feed (ipt) Cutter Diameter (in)			
			1/4	1/2	3/4	1-2			1/4	1/2	3/4	1-2
.050	M2, M7	75	.001	.002	.003	.004	C6	240	.001	.002	.004	.006

### Tapping

High Speed Tools	
Tool Material	Speed (fpm)
M1, M7, M10	10-20

### Broaching

High Speed Tools		
Tool Material	Speed (fpm)	Chip Load (ipt)
T15, M42	15	.002

### Additional Machinability Notes

When using carbide tools, surface speed feet/minute (SFPM) can be increased between 2 and 3 times over the high speed suggestions. Feeds can be increased between 50 and 100%.

Figures used for all metal removal operations covered are average. On certain work, the nature of the part may require adjustment of speeds and feeds. Each job has to be developed for best production results with optimum tool life. Speeds or feeds should be increased or decreased in small steps.

### Grinding and Polishing

In cutlery applications, grinding and polishing are very important. Carpenter Stainless Type 440B works well in these operations but considerable care must be used not to overheat since the corrosion resistance may be lowered.

### Weldability

Because of its high hardness capability, this steel is seldom welded. However, if welding is necessary, the parts should be preheated and maintained at about 500°F (260°C), welded, and then immediately given a 6-8 hour anneal at 1350/1400°F (732/760°C) with a slow furnace cool. The parts should not be allowed to cool below 500°F between welding and annealing. High welding heat inputs should be used. To obtain mechanical properties in the weld similar to the base metal, welding consumables of like composition should be considered. Otherwise, AWS E/ER309 should be considered.

### Other Information

#### Applicable Specifications

- ASTM A276
- ASTM A473
- ASTM F899
- ASTM A314
- ASTM A580
- QQ-S-763

#### Forms Manufactured

- Bar-Rounds
- Strip
- Wire-Rod
- Billet
- Wire

#### Technical Articles

- [A Guide to Etching Specialty Alloys for Microstructural Evaluation](#)
- [How to Passivate Stainless Steel Parts](#)
- [Passivating and Electropolishing Stainless Steel Parts](#)
- [Unique Properties Required of Alloys for the Medical and Dental Products Industry](#)

#### Disclaimer:

The information and data presented herein are typical or average values and are not a guarantee of maximum or minimum values. Applications specifically suggested for material described herein are made solely for the purpose of illustration to enable the reader to make his/her own evaluation and are not intended as warranties, either express or implied, of fitness for these or other purposes. There is no representation that the recipient of this literature will receive updated editions as they become available.

Unless otherwise specified, registered trademarks are property of CRS Holdings Inc., a subsidiary of [Carpenter Technology Corporation](#)  
Copyright © 2020 CRS Holdings Inc. All rights reserved.

Visit us on the web at [www.carttech.com](http://www.carttech.com)

Edition Date: 04/01/1987